

Bio Bleach soft



Technical Data Sheet

Intended Use: Thermoforming blank for bleaching- and pharmaceutical splints

Manufacturer: Dreve Dentamid GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	Chemische Bezeichnung
1	Ethylen und Venylacetat

Physikalische Eigenschaften:

Colour: transparent
Thickness: 1,00 mm
Diameter: Ø 120 mm (Sonderabmessungen auf Anfrage)
Density: 0,935 g/cm³ DIN 53479
Elongation at break: > 750% DIN 53455
E-Modul: 75 MPa DIN 53457
Melting temperature: 92 °C D.S.C.
Flexural strength: 19 MPa DIN 53457
Hardness: 92 Shore A

Dreve Dentamid GmbH
Max-Planck-Str. 31
59423 Unna / Germany
Tel.: 02303 / 8807-0
Fax: 02303 / 8807-55
dentamid@dreve.de
www.dreve.com